

EARTHKEEPER® HYDRAULIC OIL BIODEGRADABLE HYDRAULIC OIL

Earthkeeper® Hydraulic Oil is a premium quality, environmentally responsible hydraulic fluid designed to provide exceptional performance in both industrial and mobile hydraulic systems. This vegetable based formulation satisfies the most rigorous criteria for biodegradability and low toxicity. Earthkeeper® Hydraulic Oil has the necessary anti-wear characteristics for hydraulic systems operating under high load and high pressure. It is also treated with additives that protect against rust and corrosion.

Earthkeeper® Hydraulic Oil meets the definition of a biobased lubricant as outlined in section 9001 of The Farm Security and Rural Investment Act (FSRIA) of 2002 (Public Law 107-171/ HR 2642) and qualifies for preferred procurement by U.S. Federal Agencies as set forth in FSRIA section 9002.

Earthkeeper® Hydraulic Oil has been certified by the USDA as biobased, and has earned USDA BioPreferred designation.

BENEFITS:

- WEAR PROTECTION – equal or superior to conventional mineral oil based fluids
- RUST PROTECTION – protects against rust and corrosion.
- TEMPERATURE STABLE – easy cold starts and less thinning out at high temperatures.
- SECURITY – easily passes all tests for biodegradability and is classified as “Readily Biodegradable”.

APPLICATIONS:

Earthkeeper® Hydraulic Oil is suitable for use in all hydraulic systems and anywhere a vegetable-based lubricant is preferred.

ASTM #	Grade	TYPICAL CHARACTERISTICS				
		ISO 32	ISO 46	ISO 68	ISO 100	ISO 150
D-445	Kinematic Viscosity					
	cSt @ 40°C	34.15	47.26	70.10	99.00	141.80
	cSt @ 100°C	7.85	10.82	15.67	21.08	29.00
D-2161	Saybolt Viscosity					
	SUS @ 40°C	172.20	236.64	350.20	495.00	710.00
	SUS @ 100°C	52.44	62.94	81.92	105.00	141.00
D-2270	Viscosity Index	212	229	239	240	245
D-97	Pour Point, °F (°C)	<-30 (-34)	<-30 (-34)	<-30 (-34)	<-30 (-34)	<-30 (-34)
Gardner Method	Density, lb/gal @ 60°F (15.5°C)	7.68	7.68	7.68	7.70	7.70
	Specific Gravity, g/cc @ 60°F (15.5°C)	0.9212	0.9212	0.9212	0.9236	0.9236
D-92	Flash Point, °F (°C) Cleveland Open Cup	415 (213)	420 (216)	410 (210)	415 (213)	415 (213)
D-4172	Four Ball Wear Scar Wear, mm	0.39	0.40	0.45	0.53	0.48
D-665	Rust Test	Pass	Pass	Pass	Pass	Pass
D-130	Copper Strip Corrosion 212°F (100°C) @ 3 hr	1B	1B	1B	1B	1B

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

PACKAGING

Shuttle Tanks	Drums	Pails
---------------	-------	-------

For warranty information, scan the QR code.
You can also email us at sales@whitmores.com
Or write to the Sales Department at the address below.

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 800-699-6318
An ISO 9001 and ISO 14001 registered company • www.whitmores.com

